






INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : A61K 9/16</p>	<p>A1</p>	<p>(11) International Publication Number: WO 99/26605</p> <p>(43) International Publication Date: 3 June 1999 (03.06.99)</p>
<p>(21) International Application Number: PCT/US98/24260</p> <p>(22) International Filing Date: 13 November 1998 (13.11.98)</p> <p>(30) Priority Data: 09/977,093 24 November 1997 (24.11.97) US</p> <p>(71) Applicant: THE TRUSTEES OF THE UNIVERSITY OF PENNSYLVANIA [US/US]; Suite 300, 3700 Market Street, Philadelphia, PA 19104 (US).</p> <p>(72) Inventors: DUCHEYNE, Paul; 763 Applegate Lane, Rosemont, PA 19010 (US). RADIN, Shulamith; 8 Brookview Drive, Voorhees, NJ 08043 (US).</p> <p>(74) Agents: MACKIEWICZ, John, J. et al.; Woodcock Washburn Kurtz Mackiewicz & Norris LLP, 46th floor, One Liberty Place, Philadelphia, PA 19103 (US).</p>		<p>(81) Designated States: CA, JP, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published With international search report.</p>
<p>(54) Title: CONDITIONING OF BIOACTIVE GLASS SURFACES IN PROTEIN CONTAINING SOLUTIONS</p> <div style="text-align: center;">   <p>8</p> </div> <div style="text-align: center;">  <p>A</p> </div> <p>(57) Abstract</p> <p>Conditioning of the surface of silica-based glass or ceramic by differential immersion in a serum protein-containing solution, and the resultant microporous Ca-P surface layer having serum-protein like organic molecules, as defined herein intermingled throughout (Fig. 6A) is described.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

CONDITIONING OF BIOACTIVE GLASS SURFACES IN PROTEIN CONTAINING SOLUTIONS

Reference to Related Applications

This application is a continuation-in-part of Application Serial No. 08/647,171,
5 filed May 9, 1996, (currently pending) which is incorporated herein by reference in its
entirety.

Field of the Invention

This invention relates to materials comprising silica-based glass or ceramic
compositions having been treated to form a microporous calcium-phosphate (Ca-P)
10 surface layer having serum-protein like organic molecules, as defined herein,
intermingled throughout and, optionally, other biologically active molecules intermingled
throughout and/or adsorbed thereon.

Government Rights

The invention disclosed herein was made with Government support. The United
15 States government may have rights to certain aspects of this invention.

Background of the Invention

In U.S. Patent No. 5,204,106, issued to Schepers et al., (hereby incorporated
by reference) the implantation of bioactive glass granules having the composition: 45 %
SiO₂, 24.5 % Na₂O, 24.5 % CaO and 6 % P₂O₅, and a size range of 280-425 μm in
20 diameter into the jaw of beagle dogs is disclosed. With particles of this size range,
internal pouches formed in each of the particles and, subsequently, osteoprogenitor cells
differentiated into osteoblasts within the pouches, actively laying down bone tissue.
Next, bone tissue proliferated from the excavations, surrounded the particles and

- 2 -

connected with bone tissue being formed around neighboring particles. Bone tissue was formed within the particle, without being bridged to the lingual or buccal bone plates. At 3 months, bone had grown throughout the surgical defects treated with glass granules. A similar phenomenon was not observed with particles of a larger size range, i.e., ~480-5 800 micrometers, or a smaller size range, i.e., ~210-300 micrometers.

Glass granules of narrow size range (300 - 360 μm) were used in a clinical trial in humans. Schepers et al., "Bioactive Glass Particles of Narrow Size Range: A New Material for the Repair of Bone Defects," *Implant Dentistry*, 2(3):151-156, 1993, incorporated herein by reference. In this clinical study, 87 patients and 106 maxillo 10 facial defects were treated. At 3 months, the application sites had fully solidified. At six months, no radiological difference between the defect sites and the surrounding bone could be discerned.

It was subsequently discovered that particles in the size range 200-300 micrometers effected the same results if implanted into sites exhibiting a reduced 15 metabolic state, particularly as compared to the maxillo-facial sites. Such sites are found, for example, in the appendicular skeleton, and in certain disease states. U.S. Application Serial No. 08/268,510, hereby incorporated by reference.

The *in vivo* event which initiates the reactions leading to the formation of bone throughout the defects is an excavation of the particles. The excavation is the result of 20 physico-chemical reactions taking place in the glass, as well as a cell-mediated resorption of the internal reaction layer. Bioactive glass reacts at its surface with the formation of two reaction layers: a silica gel below the surface and a Ca-P rich layer at the surface.

It has now been discovered that differential immersion of other geometric forms of melt- or sol-gel-derived silica-based glass or ceramic in aqueous solutions containing 25 serum-protein like organic molecules, as defined herein, results in a microporous surface layer of Ca-P having the serum-protein like organic molecules intermingled throughout. It is expected that silica-based glass or ceramic so conditioned will have an improved performance *in vitro* and *in vivo*, e.g., in relation to cell phenotype expression and attachment of cells in general. Prior treatments did not achieve this surface layer.

Summary of the Invention

According to the present invention, silica-based glasses or ceramics are conditioned to achieve a microporous Ca-P surface layer having serum-protein like organic molecules, as defined herein, intermingled throughout and, optionally,
5 biologically active molecules intermingled throughout and/or adsorbed thereon.

In one aspect, the present invention relates to a method for modifying the surface of silica-based glasses or ceramics by differential immersion in aqueous solutions containing serum-protein like organic molecules to achieve a microporous Ca-P surface layer having serum-protein like organic molecules intermingled throughout.

10 In yet another aspect, the present invention relates to a material comprising silica-based glasses or ceramics having a microporous Ca-P surface having serum-protein like organic molecules herein intermingled throughout, prepared by differential immersion of the silica-based glasses or ceramics in aqueous solutions containing serum-protein like organic molecules.

15 In a further aspect, the present invention relates to a material comprising silica-based glasses or ceramics having a microporous Ca-P surface layer having serum-protein like organic molecules intermingled throughout.

Brief Description of the Drawings

Figures 1a-c depict the changes in Si, Ca, and P content, respectively, during
20 immersion of sol-gel derived particles as a function of glass composition.

Figure 2 is a Scanning Electron Micrograph depicting a hollow calcium-phosphate particle formed from sol-gel derived glass.

Figure 3 depicts changes in Si content during immersion of sol-gel derived particles of S70 glass composition as a function of particle size.

25 Figure 4 depicts the effect of serum on amount of Si released for S70 sol-gel derived glass particles.

Figures 5a-c are SEM, EDXA, and FTIR, respectively, depicting the changes in morphology, composition and structure, respectively, of the surfaces following differential immersion in serum-containing solution.

- 4 -

Figures 6a-c are SEM, EDXA, and extended carbon peaks of a cross-section of a granule following differential immersion in serum-containing solution.

Figures 7a-c are SEM, EDXA, and FTIR, respectively, depicting the changes in morphology, composition and structure, respectively, of the surfaces following differential immersion in serum-free solution.

Figures 8a-c are SEM, EDXA, and FTIR, respectively, depicting the changes in morphology, composition, and structure, respectively, of the surfaces following integral immersion in serum-free solution followed by immersion in serum-containing solution.

Figure 9 is an RBS of a sample following integral immersion in serum-free solution followed by immersion in serum-containing solution.

Figures 10a-d are SEM, EDXA (b and c), and FTIR, respectively, depicting the changes in morphology, composition, and structure, respectively, of the surfaces following integral immersion in serum-containing solution.

Detailed Description

The materials treated according to the present invention can be used in a variety of applications including, without limitation, to fill bony defects in sites present throughout the body of vertebrates for stimulating growth and repair. The materials can be used for the *in vitro* growth of bone and other tissues. The materials can also be used *in vitro* or *in vivo* with anchorage dependent cells or at sites with such cells. The materials are formed as a result of conditioning silica-based glass materials containing calcium and phosphate *in vitro*.

As used herein, "silica-based" refers to the inclusion of a silicon oxide in the composition of the glass. Other oxides may also be present.

"Bioactive" as used herein refers to a bone bioactive material having a calcium phosphate rich layer present, or which develops during appropriate *in vitro* or *in vivo* conditions. As observed by Pereira et al., J. of Biomed. Mat. Res., (1994) 28:693-698 (incorporated herein by reference), pure silica gel having a porous hydrated layer is able to induce a carbonated hydroxyapatite layer when soaked in a simulated body fluid containing calcium and phosphate ions. Pure silica hydrogels produced using TEOS and

- 5 -

drying temperatures of around 400°C were immersed in simulated body fluids having different magnesium, calcium, and phosphate ions. It was reported that apatite nucleation induction periods were decreased with the addition of small amounts of calcium and phosphate ions to the fluids, as well as increase in pH. Li et al., J. Appl. Biomater., (1993) 4:221-229 and Li et al., J. Amer. Ceram. Soc., (1993) 75:2094-2097 (both incorporated herein by reference).

Melt-derived silica-based, calcium and phosphate containing materials to be conditioned according to the present invention can be prepared following, for example, the procedure disclosed in U.S. Patent No. 5,204,106, hereby incorporated by reference.

10 The composition for the melt-derived glass can be as follows (in weight percent): SiO₂ - 40-60; Na₂O - 10-32 CaO - 10-32 and P₂O₅ - 0-12. The composition for the melt-derived glass can also be SiO₂ - 39-70; Na₂ - 0-25; CaO - 8-20; and P₂O₅ - 0-6. Brink, Maria, J. Biomed. Mat. Res., 36: 109-117, 1997, incorporated herein by reference.

Other compounds, and oxides, may also be present, such as described in P. Ducheyne, 15 "Bioglass coatings and bioglass composites as implant materials," J. Biomed. Mat. Res., 19:273-291, 1985, incorporated herein by reference.

The sol-gel derived materials can be prepared following, for example, the procedures disclosed in U.S. Patent No. 5,591,453, hereby incorporated by reference.

The compositional range for the sol-gel derived glass can be as follows (in weight 20 percent): SiO₂ - 60-100; CaO - 0-40; and P₂O₅ - 0-10.

The *in vitro* excavation of the silica-based, Ca-P containing glass granules and transformation into Ca-P shells disclosed in prior application Serial No. 08/647,171 was achieved by differential immersion of the glass granules in, *inter alia*, serum- containing solutions which provoked the dissolution of silicon from the glass matrix. Similar 25 conditioning can be applied to other geometric forms of melt- and sol-gel-derived bioactive glasses, including, but not limited to, disks, blocks, monoliths, fibers, coatings, and rods, resulting in a novel surface. Differential immersion can be achieved by periodic solution exchange in a system in which the solution is static, or by use of a dynamic system in which the immersion solution is continuously supplied as a flow of 30 fresh solution. See, U.S. Patent No. 5,002,890, issued to Dennis R. Morrison on

- 6 -

March 26, 1991 for an example of how to achieve dynamic fluid replenishment in, that case, tissue culture.

The immersion conditions such as, for example, solution composition, duration, number of solution exchanges, material weight to solution volume ratio (W/V), can vary to a great degree as long as the formation of the calcium phosphate layer is perpetuated. The appropriate conditions to achieve the invention described herein can be readily determined by one skilled in the art.

The immersion conditions for the *in vitro* excavation were previously selected to allow the following events to occur: 1) formation of a surface Ca-P layer; and 2) continuous dissolution of the silica-network, remaining under the Ca-P layer, until about 80 to 100% of the original Si content in the glass is dissolved. In order to stimulate the continuous silica network dissolution, the solution used for the immersion must remain undersaturated with respect to soluble silica. Events 1) and 2) can be achieved by consecutively different solutions. For example, in the case of a glass composed of 100% silica, a calcium-phosphate surface layer must first be formed. This can be accomplished by immersing the glass in solutions saturated in silicon, such as described in U.S. Application Serial No. 08/647,007 (our docket UPN-2745), hereby incorporated by reference.

The immersion conditions for conditioning the silica-based glass and ceramics according to the present invention are similar. The exchange of solution perpetuates the formation of the microporous Ca-P surface layer having serum-protein like organic molecules, as defined herein, intimately intermingled throughout.

Once this microporous Ca-P surface layer is formed, subsequent immersions can be performed in aqueous solutions containing other biologically active molecules, with or without the serum-protein like organic molecules, as defined herein, present. The subsequent immersions can be performed in an integral mode, as defined herein, and are performed for a time sufficient to allow adsorption of the biologically active molecules onto the surface of the microporous Ca-P surface layer, including within the pores. For example, immersion times of from about 5 minutes to about 160 hours are contemplated.

- 7 -

The following reactions are involved in the transformation of the melt-derived glass: hydrolysis and formation of a silica-gel layer; migration of Ca and PO_4 ions from the bulk through the Si-gel to the surface; accumulation of the ions at the surface and formation of a Ca-P rich surface; continuous growth of the Si-gel and Ca-P rich layers; and continuous silica dissolution.

The following reactions are involved in the transformation of sol-gel derived glass granules: loss of soluble silica along with migration of Ca and PO_4 ions through highly porous glass to the surface; leaching of the ions to a solution along with partial accumulation at the surface; formation of a CaP- surface layer; growth of the CaP-layer along with continuous silica dissolution.

Some aqueous solutions which can be used include, but are not limited to, the following:

- a) water;
- b) ion-free, Tris buffer, with an initial pH of from about 6.8 to about 8.0 - for melt-derived bioactive glass;
- c) phosphate buffer solution with an initial pH of from about 6.8 to about 8.0; and
- d) Tris or phosphate buffer solutions containing varying concentrations of Ca and PO_4 (HPO_4 or H_2PO_4) with or without addition of varying concentrations of other ions including, but not limited, to Na, K, Cl, CO_3 , and Mg, or their combination.

Solution d) is used when the glass or ceramic is 100 % silicon oxide. The immersion solution must also contain serum-protein like organic molecules, as defined herein, which result in the formation of a microporous Ca-P surface layer. The immersion solution can also contain biologically active molecules as define herein, and/or such molecules can be adsorbed after formation of the microporous Ca-P surface layer.

With increasing stability of the silica-based glass -- such as increasing the amount of network former SiO_2 , increasing the amount of network modifiers that render the network more stable (see Ducheyne, *supra*), or, in the case of melt-derived glass, replacing Na_2O with a more stable alkali oxide -- the duration of treatment and/or the number of solution exchanges will have to be increased, or the material size will have to

be reduced. The presence of serum-protein like organic molecules in the immersion solution decreases the dissolution rate. A possible explanation is that the adsorption of the proteins on the surface of the glass modifies the surface of the glass in contact with solution.

5 The dissolution of various forms of solid silica in aqueous solutions has been the focus of several studies. O'Connor et al., "The kinetics for the solution of silica in aqueous solutions," *J. Phys. Chem.*, 62:1195-8, 1958; and Iler, R.K., The Chemistry of Silica: Solubility, Polymerization, Colloid and Surface Properties, and Biochemistry, Wiley, New York, 1979. It has been established that any form of solid silica in contact
10 with aqueous solutions dissolves into monosilicic acid Si(OH)_4 until the solution reaches saturation. By exchanging the immersion solution such that saturation is never reached, the diffusion process is favored and thus dissolution is enhanced. The *in vitro* dissolution behavior during the differential immersion is expected to be similar to that observed *in vivo*, during which the body fluid is continuously replenished.

15 "Microporous Ca-P surface layer" as used herein refers to a surface layer containing calcium and phosphorous. Other compounds, for example, silicon, may also be present.

As used herein, the term "about" means approximately $\pm 10\%$, except when referring to immersion times, in which case about means \pm a day or two.

20 "Serum-protein like organic molecules", as defined herein, refers to organic molecules having the same effect as serum proteins following differential immersion of silica-based glass or ceramic therein, i.e., resulting in the formation of a microporous Ca-P surface layer. Serum-protein like organic molecules according to the present invention can be readily determined by those skilled in the art following the disclosure
25 herein. Serum-protein like organic molecules produced by synthetic means, including genetic engineering, are included in the present invention, as are derivatives containing the active domains of said organic molecules, e.g., the binding domains of attachment molecules. When present during differential immersion, serum-protein like organic molecules slow down the Ca-P precipitation which protects the underlying glass network
30 from degradation during dissolution. The Ca-P layer is also microporous and, thus, there is not sufficient protection of the underlying glass network, and dissolution of

- 9 -

silicon and formation of a Ca-P layer at the surface continues with solution replenishment. Combinations of serum-protein like organic molecules are also included.

The term "bony defect", as used herein, refers to regions necessitating growth or repair including, but not limited to, fractures, areas of erosion or degradation, osteolysis, holes resulting from removal of screws and pins, replacements, periodontal applications, and deterioration of bone due to old age or disease.

As used herein, "biologically active molecules" are defined as those organic molecules having an effect in a biological system, whether such system is *in vitro*, *in vivo*, or *in situ*. Biologically active molecules include, but are not limited to, the following categories: growth factors, cytokines, antibiotics, anti-inflammatory agents, analgesics and other drugs, and cell attachment molecules. It is contemplated that many serum-protein like organic molecules will also function as biologically active molecules, and vice versa.

The term "antibiotic" includes bactericidal, fungicidal, and infection-preventing drugs which are substantially water-soluble such as, for example, gentamicin, vancomycin, penicillin, and cephalosporins.

The term "growth factors" refers, without limitation, to factors affecting the function of cells such as osteogenic cells, fibroblasts, neural cells, endothelial cells, epithelial cells, keratinocytes, chondrocytes, myocytes, cells from joint ligaments, and cells from the nucleus pulposus. Platelet derived growth factors (PDGF), the transforming growth factors (TGF- β), insulin-like growth factors (IGFs), fibroblast growth factors (FGFs), and the bone morphogenetic proteins (BMPs) are examples of growth factors encompassed in the various geometric forms according to the present invention.

The term "cell attachment molecules" as used herein includes, but is not limited to, fibronectin, vitronectin, collagen type I, osteopontin, bone sialoprotein, thrombospondin, and fibrinogen. Such molecules are important in the attachment of anchorage-dependent cells to the tissue matrix or to implant materials.

The term "intermingled throughout" as used herein means that the molecules, e.g., serum-protein like organic molecules, as defined herein, are distributed throughout

- 10 -

the microporous Ca-P surface layer and are not just adsorbed on or embedded in on its surface.

The term "microporous" as used herein refers to a pore size of from about 0.1 to about 10 μm .

5 The term "macroporous" as used herein refers to a pore size of from about 40 to about 1000 μm .

The term "dense" as used herein in reference to a glass or ceramic means substantially non-porous.

Previously, we proposed to treat the bioactive glass with a two step treatment
10 (see U.S. Patent No. 5,643,789). We treated bioactive glass because we found that creating a Ca-P surface on which proteins were adsorbed stimulated the expression of the osteoblast phenotype. However, the Ca-P layer which is created is relatively thin, in contrast to the layer one observes on bioactive glass after *in vivo* implantation. In addition, the Ca-P and protein are not mixed together as would be the case when the
15 layer is formed *in vivo*. In this previously invented two-step conditioning treatment, the first step of the treatment is performed in protein-free medium and quickly leads to the formation of a protective Ca-P film which prevents the corrosion reactions from proceeding deeper and deeper into the material. Further, since the proteins are only adsorbed in a second step, the protein layer is adsorbed only on top of the Ca-P layer.

20 Immersing the bioactive glass in a solution containing serum without changing the solution during the immersion period -- i.e., an integral immersion as the term is used herein -- did not produce the desired composite organic-inorganic layer -- i.e., a layer with intermingled Ca-P and serum-protein like organic molecules. Further, we found that the kinetics of the formation of the Ca-P surface reaction layers were
25 extremely slow in comparison with its formation in an electrolyte solution without serum. Others before us had also used tissue culture solutions to study reaction layer formation on bioactive glasses.

In the present invention, we disclose a microporous Ca-P surface layer intermingled with serum-protein like organic molecules. Furthermore, this invention
30 includes the methodology to obtain relatively thick Ca-P-serum-protein like organic

- 11 -

molecule layers, which can be digested by cells. The thicker Ca-P-serum-protein like organic molecule layer for digestion by cells is expected to have a beneficial effect.

We propose that the carbonated hydroxyapatite layer typically observed on bioactive glass after implantation is formed as a result of activity of bone cells adhered onto the initial reaction layer. This reasoning follows from two sets of experiments in our laboratory. We showed that, prior to the formation of a carbonated hydroxyapatite layer, an amorphous Ca P layer, intermingled with Si, forms. Performing Fourier transform infrared spectroscopy on two sets of glass samples after identical experimental conditions except for the presence of neonatal rat calvaria osteoblasts, we also found either no evidence of carbonated hydroxyapatite (no cells present), or very clear evidence (with osteoblasts) (El-Ghannam et al., *J.Biomed.Mat.Res.*, 29: 359-370, 1995). Furthermore, using energy dispersive X-ray analysis, we measured significant differences in elemental concentration on one sample after two days of osteoblast culture between areas covered by extracellular matrix elaborated by the cells, and those areas not yet covered (El-Ghannam et al., *Biomat.*, 18:295-303 (1997). Prominent Ca, P and Si peaks were evident under the extracellular matrix. Areas not covered by matrix revealed small Si and P peaks and a pronounced Ca peak. Noteworthy, it is not just the interaction of the initial surface reaction layer with cells, but also the intriguing presence of Si in those areas where there is marked cellular activity.

Furthermore, having the serum-protein like organic molecules intermingled throughout the surface is expected to be beneficial as well. It has been previously reported that adsorbed, nonspecific proteins at a bone site are regularly eliminated from the ceramic surface due to cellular degradation (Rohanizadeh et al., *Bioceramics*, 10:27-30, 1997). Accordingly, a thick layer of Ca-P having proteins intermingled throughout will stimulate additional cellular activity.

We have now found that if we continuously replenish the immersion solution in which the surface reaction layer is formed, we perpetuate the reaction at the glass or ceramic surface and continue to form an increasingly thicker layer of microporous Ca-P intermingled with organic compounds of the immersion solution. Furthermore, the microporous Ca-P surface layer forms even when the glass or ceramic to be treated is not itself porous, i.e., is dense.

- 12 -

Replenishing the solution can be achieved by immersing the glass objects in a volume of solution in, for example, a vial or receptacle and exchanging the solution from time to time either through a partial or total solution exchange. Alternatively, the glass or ceramic to be surface-treated can also be placed in a system that permits
5 continuous flow of the treatment solution past the glass surfaces, such as are discussed above.

The surface layers and the methods for making these are extremely useful in any application where cells make contact with the material by virtue of the stimulatory nature of the surfaces on cell function. By now having a surface that is a continuous
10 mixture of Ca-P and serum-protein like organic molecules, there is a continual intra- and extra-cellular effect arising from both the chemical components of the mineral phase of bone as well as the serum-protein like organic molecules. This effect will greatly stimulate tissue engineering procedures *in vitro* and *in vivo*. Bone tissue engineering procedures will particularly benefit from these new and unexpected findings. Further,
15 any anchorage dependent cell can be placed in contact with the newly developed surface reaction layer.

In our invention there is the added advantage that silicon is incorporated throughout the surface reaction layer in tandem with the serum-protein like organic molecules. No other treatment leads to the simultaneous incorporation of both. Data
20 using our prior two-step treatment indicates the presence of prominent Si and P peaks, in addition to a Ca peak, only under extracellular matrix elaborated by osteoblast cells in culture on bioactive glass. El-Ghannam et al., *J. Biomed. Mat. Res.*, 29:359-370 (1995) and El-Ghannam et al., *Biomat.*, 18:295-303 (1997).

Others have suggested that silicon is associated with calcium in an early stage of
25 bone formation. Carlisle found that silicon is required for normal growth and development in the chick. E.M. Carlisle, *Science*, 167:279-280 (1970) and E.M. Carlisle, *Science*, 178:619-621 (1972). Schwarz et al. reported that silicon deficiency in the rat resulted in depressed growth and skull formation. Schwarz et al., *Nature*, 239:333-334 (1972). Later, Carlisle reported that silicon's primary effect is on the
30 matrix, i.e., that silicon is required for collagen and glycosaminoglycan formation. Carlisle also noted that additional support for silicon's metabolic role in connective tissue

- 13 -

was provided by the finding that silicon is a major ion of osteogenic cells and is present in especially high concentrations in the metabolically active state of the cell and that, further, silicon reaches relatively high levels in the mitochondria of these cells. E.M. Carlisle, *Ciba Foundation Symposium*, 121:123-139 (1986).

5 As is disclosed below, the composition and morphology of the surface of the invention are different from that formed by immersion in a serum-free medium, followed by an immersion in serum. Using the method according to the invention, we found that the reaction surface comprises a microporous Ca-P surface layer having serum-protein like organic molecules, intermingled throughout. The surface layer formed in serum has
10 a lower Ca/P ratio (about 1.2-1.3) than the surface formed in serum-free solutions (> 1.45) and contains significant amounts of Si of which it was previously suggested to have an effect on bone cell function. The invention lies in the achievement of this reaction surface.

The method to create these beneficial reaction layers on silica-based glass or
15 ceramic, e.g., bioactive glass, is typically as follows. The solution containing the serum-protein like organic molecules can comprise serum. The serum source can be, without limitation thereto, human, bovine, porcine, etc. Differential immersion (immersion with solution exchange at designated time periods) in serum-containing, buffered (pH 7 - 7.6) solutions such as Tris or phosphate buffered solution, either ion-
20 free or containing ions similar to those found in human plasma. Serum content can vary from about 1% to about 100%, preferably from about 8% to about 100%. The total protein content in serum generally can vary from about 3.0% to about 9.0%. Accordingly, when the immersion solution does not comprise serum, concentrations of the serum-protein like organic molecules from about 0.03%, preferably about 0.08%,
25 and greater can be used. The immersion solution can additionally contain other biologically active molecules, as defined herein, including but not limited to attachment molecules, growth factors, collagen, etc.

The total immersion time can vary from about 1 hour up to about two weeks. Depending on the desired surface composition and thickness of the reaction layer(s), and
30 concentration of serum-protein like organic molecules, shorter or longer immersion times may be appropriate. The immersion times and conditions can be readily ascertained by

- 14 -

persons of ordinary skill in the art. The differential immersion process involves either the continuous flow of solution past the treatment surface or the periodic replenishment of the solution. The solution is an aqueous medium (with or without electrolytes) supplemented with serum-protein like organic molecules, as defined herein.

5 The method can be performed upon melt- or sol-gel-derived dense or macroporous glass or ceramic with a similar result. The resultant surface has a microporous structure, e.g., having pore sizes from about 0.1 μm to about 10 μm of uniform pore size.

 The immersion experiments reported herein demonstrate major differences
10 between surface modification of bioactive glass by differential immersion in serum-containing solutions, in comparison to those which occur upon integral immersion in either serum-free or serum-containing solutions. The differential immersion in serum-containing solutions allows one to overlay a surface layer with unique properties, i.e. to create a microporous Ca-P surface layer having organic molecules intermingled
15 throughout.

 The microporous surface allows the elements of tissues to penetrate into the micropores upon implantation. Further, the porous structure facilitates a controlled release of molecules intermingled throughout and, optionally, adsorbed thereon in a subsequent treatment. Additionally, the pores provide a greater surface area for
20 interaction with body fluids upon implantation.

 The differential immersion enhances formation of crystalline Ca-P phases with similar characteristics as the mineral phase of bone, particularly in comparison to the integral immersion in serum protein-containing solutions. Indeed, FTIR analysis showed formation of crystalline Ca-P phases after differential immersion (1 week) in
25 serum-containing solution (Fig. 7c). In contrast, Ca-P phases present in the surface layer after integral immersion for the same time period were amorphous (Fig. 10d).

 In comparison, integral immersion in serum protein-containing solutions created a smooth, dense, fragile and amorphous surface consisting of a silica layer and a silica matrix with accumulated calcium and phosphate.

30 In contrast to differential immersion in serum-containing solution, differential

- 15 -

immersion in serum-free solution produced a dense surface layer composed of closely packed Ca-P precipitates which cannot be intermingled with proteins.

Example 1 below describes the excavation of particles using differential immersion under conditions similar to the present invention. An example of
 5 conditioning according to the present invention, with comparison to other conditioning methods, is provided in Example 2 below.

Example 1

Transformation of sol-gel-derived glass 45S5 granules into hollow Ca-P shells using Differential Immersion

10 Specimens prepared according to Example 1 of Application Serial No. 08/647,171 were immersed in three solutions: TE, TE supplemented with 10% serum (vol%), and 100 % serum. Newborn calf serum was used. The solutions were chosen to address effect of important constituents of the *in vivo* milieu. Immersions were performed in vials. TE is a non-proteinaceous control that contains the electrolyte
 15 constituents of human blood plasma in similar concentrations (cf. Table I). TE was prepared by dissolving reagent grade NaCl, KCl, NaHCO₃, MgCl₂·6H₂O, MgSO₄·7H₂O, KHPO₄anh. and CaCl₂·2H₂O in a 0.05 M Tris [hydroxymethyl] aminomethane hydrochloride buffered solution. The resulting pH was 7.4 at 37°C.

Table I

Ionic content of human blood plasma and TE.

Ion	Human blood plasma (mM)	TE (mM)
Ca ²⁺	2.5	2.5
HPO ₄ ²⁻	1.0	1.0
Na ⁺	142.0	152.0
25 Cl ⁻	103.0	136.0
K ⁺	5.0	5.0
Mg ²⁺	1.5	1.5
HCO ₃ ⁻	27.0	27.0
SO ₄ ²⁻	0.5	0.5

- 16 -

A differential immersion was effected by exchange with fresh solution at various time points throughout the duration of immersion. In the present example, the samples were exposed to fresh solution after 3, 6, 9, 24, 48, 72, 96, 124 and 168 hours of immersion. These intervals were chosen in an attempt to maintain a maximum
 5 concentration of Si in solution less than 2/3 of the saturation concentration. The immersion protocol was intended to reflect the continuous replenishment of body fluid at the implant site. The samples were immersed for up to 7 days.

Three samples were tested per set of conditions. The weight to solution volume ratio was 0.5 mg/ml. The samples were placed in an incubator at 37°C in a 5% CO₂
 10 atmosphere and continuously shaken (200 revolutions/minute). The vials were loosely capped to minimize evaporation without preventing gas exchange.

The testing conditions (i.e., sample, immersion mode, and solution) and the parameters studied are listed in Table II. Upon completion of the selected immersion protocols, the solutions were collected and the retrieved particles were rinsed with
 15 ethanol and dried in ambient air.

Table II
Testing conditions

Composition	Particle size	Solution
S100 S100V S70	500-710 μm	TE
S70	210-500 μm	TE
S70	500-710 μm	TE TE+10%serum serum

The Si and Ca concentrations were measured by flame atomic absorption
 25 spectrophotometry (FAAS, Perkin-Elmer 5100PC). The P concentration was determined using a colorimetric method (Heinonen et al., "A new and convenient colorimetric determination of inorganic orthophosphate and its application to the assay of inorganic

- 17 -

pyrophosphate," *Anal. Biochemistry*, 113:313-7, 1981,) (Molybdenum yellow) (Pharmacia LKB Ultrospec Plus Spectrophotometer).

The cumulative variation of the Si, Ca, and P concentration in TE as a function of time of immersion is shown in Figures 1a-c. The error bars represent the standard deviation of the means. As is evident from Figure 2a, 80% of the initial silicon content is released from the S70 glass after 48 hours of immersion and no silicon remained after a 7-day period. Figures 1b and 1c show that the Si dissolution from S70 is accompanied by the formation of a Ca-P phase, as indicated by a continuous calcium and phosphate uptake from solution. For S100 glass, 60% of the initial silicon was released after 72 hours and, again, no silicon remained after a 7-day period. However, Si dissolution from S100 was not accompanied by a formation of a Ca-P phase, as indicated by the lack of uptake of calcium and phosphate from solution. The presence of Vancomycin in S100 did not affect the dissolution behavior of the composite, as indicated by the similar release profiles.

To determine the immersion-induced compositional and structural changes, the reacted particles were analyzed with the same techniques as used for the characterization. In addition, scanning electron microscopy in combination with energy dispersive x-ray analysis (SEM-EDXA, JEOL T300A) was employed.

FTIR analysis confirmed the formation of a calcium-phosphate material with the characteristics of a crystalline, carbonated hydroxyapatite similar to bone-mineral Ca-P.

SEM micrographs of S70 reacted particles show that the particles are transformed into Ca and P containing shells (see Figure 2, X 750). The sample was prepared for SEM examination by fracturing it. As a result, the interior of the particle was exposed. The SEM examination revealed that the particle had been transformed into a shell by the immersion treatment.

EDXA analysis only detected calcium and phosphorus, but no silicon. The Ca/P ratio of the shell as measured by EDXA is 1.5. The shell was approximately 10 μm thick.

Figure 3 shows the silicon release profile S70 particles of two sizes ranges.

These results indicate that the dissolution rate increases with decreasing particle size or

increasing external surface area. Moreover, the S70 particles of the smaller size range exhibit the same transformation into shell-like shape as found for the larger particles.

Figure 4 shows the dissolution behavior of S70 in TE, TE supplemented with 10% serum, and serum. The presence of serum in the immersion solution decreased the rate of dissolution. Statistical analysis revealed that the release profiles differed significantly among solutions ($p < 0.05$, analysis of variance) except for TE supplemented with 10% serum and 100% serum.

Example 2

Conditioning of bioactive glass surfaces

10 A) Modification of melt-derived glass 45S5 granules by differential immersion in serum-containing solution

Surface modification of melt-derived bioactive glass 45S5 granules having a size of about 300 to about 355 μm as obtained by sieving was conducted by differential immersion in Tris buffered (pH 7.4 at 37°C) solution supplemented by electrolytes typical for plasma (Table I) and 10% newborn bovine serum (TES) for up to 1 week. The samples were immersed at 1mg/ml weight-to-solution (W/V) ratio. The solution was exchanged at 3, 12, 24, 48, 96 and 168 hours. The post-immersion samples were dried and proceeded for the surface analysis.

Morphology, composition and structure of the surfaces, modified by differential immersion in serum-containing solution, are shown on the SEM micrograph and corresponding EDXA and FTIR spectra (Figures 5 a-c).

SEM micrograph (Fig.5a) of the surface indicates that differential immersion in serum-containing solution led to formation of a microporous surface on top of dense glass. The surface layer comprises very fine (0.2 to 1 μm) precipitates. The pore size varies from 0.5 to 3 μm . The surface was mainly composed of Ca-P phases with addition of Si (Fig. 5b). The presence of the Ca-P phases is confirmed by FTIR analysis (Fig. 5c). Split of the P-O bands, recorded on the FTIR spectrum, suggests that the Ca-P phases were crystalline. The appearance of the C=O band indicates the presence of adsorbed proteins in the surface layer.

Figures 6 a-c depict an SEM of a cross-section of a granule treated by differential immersion as described above (Fig. 6a), full EDXA spectra of the cross-section (Fig. 6b), and extended carbon peaks from the EDXA spectra. The EDXA spectra were taken in three spots located either on the outer side (O), in the middle of (M), or on the lower side, i.e., inner side, (L), of the granule. As is clear from these spectra, carbon is present throughout the particle. These results indicate that the serum proteins are present throughout the Ca-P layer, which is 25-30 microns thick in Figure 6a.

B) Modification of melt-derived glass 45S5 granules by differential immersion in serum-free solution

Bioactive glass samples as described in A) were immersed differentially in serum-free Tris buffered solution complemented by electrolytes typical for plasma (TE) for up to 1 week. The samples were immersed at 1 mg/ml W/V ratio. The solution was exchanged at 3, 12, 24, 48, 96 and 168 hours. The post-immersion samples were dried and proceeded for the surface analysis.

Morphology, composition and structure of the immersion-modified surface are shown on Figures 7 a-c.

SEM micrograph (Fig. 7a) shows the appearance of the reaction surface layer (central and left parts of the picture) on top of the fractured sample. The layer appears as dense and composed of closely packed globular precipitates. The EDXA (Fig. 7b) indicates that the precipitates comprise Ca-P phases. No significant Si-content was detected in the surface layer. Split of the P-O bands, recorded on the FTIR spectrum (Fig. 7c), suggests that the Ca-P phases were crystalline.

C) Modification of melt-derived glass 45S5 granules by integral immersion in serum-free solution followed by immersion in serum-containing solution

Bioactive glass samples as described in A) were immersed integrally (no solution exchange) in serum-free Tris buffered solution complemented with electrolytes typical for plasma (TE) for 48 hours and then re-immersed in serum-containing TES for either 1, 3 or 6 hours. After immersion the samples were dried and proceeded for surface analysis.

- 20 -

Morphology, composition and structure of the bioactive glass surface after immersion in TE for 48 hours and subsequent immersion in TES for 1 hour are shown on Figures 8 a-c. Extension of immersion in TES for up to 6 hours did not produce a significant change in the surface morphology and composition.

5 SEM micrograph (Fig. 8a) indicates that the reaction surface appears as a smooth, dense layer with patchy globular precipitates (cracks are artifacts due to drying). EDXA reveals that the surface layer has a major Si-content with addition of Ca and P (Fig. 8b). The appearance of an undivided P-O band on the FTIR spectrum suggests the Ca-P phases were amorphous.

10 The smooth reaction layer is composed of silica-matrix with Ca-P accumulations in it. Subsequent to formation of this layer Ca-P precipitation occurs on top of it.

A Rutherford backscattering spectrum (RBS) of a bioactive glass disk immersed as described above (i.e., integrally for 48 hours in TE followed by immersion in tissue culture medium containing 10 % NU serum for one hour) is depicted in Figure 9. The
15 sample was washed after immersion by using ethanol and acetone, and then air dried. The depth profile for carbon and nitrogen showed the adsorption of about 1000 monolayers of proteinaceous material onto the Ca-P layer. The surface resolution of RBS is very high. Accordingly, probing depth is typically limited to about 0.1 to 1 micrometer. The results indicate, therefore, that the proteinaceous material is
20 concentrated at the surface after such treatment and not throughout the Ca-P layer.

D) Modification of melt-derived glass 45S5 granules by integral immersion in serum-containing solution

Bioactive glass samples as described in A) were immersed integrally (no solution exchange) in serum-containing TES for 1 week. After immersion the samples were dried
25 and proceeded for the surface analysis.

Morphology, composition and structure of the immersion-modified surface are shown on Figures 10 a-d.

SEM micrograph (Fig. 10a) shows that the reaction surface appears as a smooth and dense layer (cracks are artifacts due to drying). No precipitation was observed on
30 top of this layer. EDXA spectrum on Figure 10b indicates that the layer has a major

- 21 -

Si-content (50%, atomic) with addition of Ca and P. The underlying layer, exposed in cracks, is mainly composed of silica (Fig. 10c). The appearance of an undivided P-O band on the FTIR spectrum (Fig. 10d) indicates that the Ca-P phases were amorphous.

The smooth reaction layers, formed on top of bioactive glass 45S5, are composed
5 of silica-matrix with amorphous Ca-P accumulations in it.

The foregoing examples are meant to illustrate the invention and not to limit it in any way. Those skilled in the art will recognize that modifications can be made which are within the spirit and scope of the invention as set forth in the appended claims.

All references cited herein are hereby incorporated by reference in their entirety.

- 22 -

What is claimed is:

1. A method for conditioning the surface of silica-based glass or ceramic comprising
 - a) immersing said glass or ceramic in an aqueous solution containing serum-protein like organic molecules for a period of time sufficient to form a microporous calcium-phosphate (Ca-P) surface layer having serum-protein like organic molecules intermingled throughout, and
 - b) exchanging the solution during said period of time at intervals sufficient to allow continuous formation of the microporous Ca-P layer.
2. The method according to claim 1 wherein said silica-based glass or ceramic contains calcium and phosphate.
3. The method according to claim 1 wherein said exchanging is performed by total solution exchange.
4. The method according to claim 1 wherein said exchanging is performed by continuous flow of solution.
5. The method according to claim 1 wherein said period of time is up to about two weeks.
6. The method according to claim 1 wherein said aqueous solution comprises serum.
7. The method according to claim 6 wherein the concentration of said serum in said aqueous solution is from about 1 % to about 100 %.
8. The method according to claim 6 wherein the concentration of said serum in said aqueous solution is from about 8 % to about 100 %.
9. The method according to claim 1 wherein said glass or ceramic is macroporous.

- 23 -

10. The method according to claim 1 wherein said glass or ceramic is dense.
11. The method according to claim 1 further comprising c) immersing said conditioned glass or ceramic in a second aqueous solution comprising biologically active
5 molecules.
12. The method according to claim 1 or 11 wherein said aqueous solution of steps a) and b) further comprises biologically active molecules.
13. The method according to claim 1 wherein said microporous Ca-P surface layer further comprises silicon.
- 10 14. A material comprising silica-based glass or ceramic conditioned according to the process of claim 1 wherein said conditioned material has a microporous Ca-P surface layer having serum-protein like organic molecules intermingled throughout.
15. The material according to claim 14 wherein said microporous surface layer has pores having a pore-size from about 0.1 μm to about 10 μm .
- 15 16. The material according to claim 14 wherein said glass or ceramic is bioactive.
17. The material according to claim 14 wherein said glass or ceramic is macroporous.
18. The material according to claim 14 wherein said glass or ceramic is dense.
19. The material according to claim 14 wherein said microporous surface layer further comprises biologically active molecules intermingled throughout.
- 20 20. The material according to claim 14 or 19, further comprising biologically active molecules adsorbed thereon.

- 24 -

21. The material according to claim 14 wherein said microporous Ca-P surface layer further comprises silicon.
22. A material comprising silica-based glass or ceramic having a microporous Ca-P surface layer having serum-protein like organic molecules intermingled throughout.
- 5 23. The material according to claim 22 wherein said microporous surface layer has pores having a size from about 0.1 μm to about 10 μm .
24. The material according to claim 22 wherein said glass or ceramic is bioactive.
25. The material according to claim 22 wherein said material is macroporous.
26. The material according to claim 22 wherein said material is dense.
- 10 27. The material according to claim 22 wherein said microporous surface layer further comprises biologically active molecules intermingled throughout.
28. The material according to claim 22 or 27 wherein said microporous Ca-P surface layer further comprises biologically active molecules adsorbed thereon.
29. The material according to claim 22 wherein said microporous Ca-P surface layer
15 further comprises silicon.




FIGURE 1A




FIGURE 1B

2/21




FIGURE 1C

3/21




FIG.2

4/21




FIGURE 3

5/21




FIGURE 4

6/21




FIG.5A

7/21




FIG.5B




FIG.5C

8/21




FIG.6A

9/21




FIG. 6B

10/21




FIG. 6C

11/21



FIG.7A

12/21




FIG.7B

13/21




FIG.7C

14/21




FIG.8A

15/21

Vert=

154 COUNTS

Disp=1




FIG.8B

16/21





FIG.8C

17/21

FIGURE 9



18/21




FIG.10A

19/21

Vert=

236 COUNTS

Disp=1




FIG.10B




FIG.10C

21/21




FIG.10D

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US98/24260

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) :A61 K 9/16

US CL :424/491

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 424/405, 491, 421, 422

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	LI et al. Apatite Formation Induced by Silica Gel in a Simulated Body Fluid. J. Amer. Ceram Soc. August 1992, Vol. 75, No. 8, 2094-2097.	1-29
Y	PEREIRA et al. Calcium phosphate formation on sol-gel-derived bioactive glasses in vitro. J. Biomed. Mat. Res. 1994, Vol. 28, pages 693-698.	1-29
Y	SCHWARZ et al. Growth-promoting Effects of Silicon in Rats. Nature. 06 October 1972, Vol. 239, pages 333-334.	1-29

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
A document defining the general state of the art which is not considered to be of particular relevance	*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
E earlier document published on or after the international filing date	*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being characterised as a manner skilled in the art
L document which may throw doubt on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*A* document member of the same patent family
O document referring to an oral disclosure, use, exhibition or other means	
P document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

14 JANUARY 1999

Date of mailing of the international search report

02 FEB 1999

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

NEIL LEVY

aco

Telephone No. (703) 308-1235